

Product Data Sheet

No.: IT- 2/2021/eng rev.0

Date: 17.08.2021

Page: 1/2

BMI Icopal Sp. z o. o.**98-220 Zduńska Wola****ul. Łaska 169/197**

GLASBIT G200 S40-15 SZYBKI PROFIL SBS

1. Product trade name: Base bitumen sheet GLASBIT G200 S40-15 SZYBKI PROFIL SBS

2. Specyfikacja techniczna:

PN-EN 13707 + A2:2012 IDT. EN 13707:2004 + A2:2009

Flexible sheets for waterproofing – Reinforced bitumen sheets for roof waterproofing – Definitions and characteristics.

PN-EN 13969:2006, PN-EN 13969:2006/A1:2007 IDT. EN 13969:2004 + EN 13969:2004/A1:2006

Flexible sheets for waterproofing – Bitumen damp proof sheets including bitumen basement tanking sheets – Definitions and characteristics.

3. Manufacturer: BMI Icopal Sp. z o.o., 98-220 Zduńska Wola ul. Łaska 169/197, Poland

4. Description of the product:

sheet with glass tissue reinforcement, coated with bitumen blend with mineral filler, top side and bottom side are finished with foil. The sheet is produced on the basis of “SPEED PROFILE” technology.

5. Type of application: base layer, for multilayer applications in roof waterproofing and, as Type T for damp proof insulations in wall constructions or on or under floors or ground slabs to prevent liquid water under hydrostatic pressure passing from the ground into the internal environment or from one section of the structure to another.

6. Method of application: torch applied or mechanically fastened

7. Information for users:

Conditions of application:

the roofing sheet should be applied on a roof when the temperature does not fall below 0 °C. It should not be applied: on a wet roof surface, on a roof covered with ice, during rain or snow falls or during strong wind.

Conditions of usage:

waterproofing made with the use of GLASBIT G200 S40-15 SZYBKI PROFIL SBS should be done according to a technical project complying with binding building regulations and detailed guidelines included in the manual issued by the producer.

Storage:

the rolls should be stored in rooms and should be protected against moisture and exposure to sunlight or source of heat. The rolls should be stored on an even surface in upright position, in one layer.

Transport:

the rolls should be transported in covered trucks, in upright position in one layer, protected against falling over and any other damage. Rolls should be placed in a way preventing their dislocation during transport.

Product Data Sheet

No.: IT- 2/2021/eng rev.0

Date: 17.08.2021

Page: 2/2

BMI Icopal Sp. z o. o.
98-220 Zduńska Wola
ul. Łaska 169/197

**8. Product performance:**

	Characteristic		Test method/ Classification	Units	Value or statement
1.	Visible defects		EN 1850-1	----	no visible defects
2.	Length (*)		EN 1848-1	m	≥ 7,5
3.	Width (*)		EN 1848-1	m	≥ 1,0
4.	Straightness		EN 1848-1	----	deviation: ≤15 mm / 7,5 m or proportional for other lengths
5.	Thickness		EN 1849-1	mm	4,0 ± 0,2
6.	Watertightness		EN 1928 Method A Method B	----	Watertight at 10 kPa Watertight at 60 kPa
7.	Durability	Watertightness after artificial ageing	EN 1296 EN 1928 Method B	----	Watertight at 60 kPa
		Chemical resistance	EN 1928 EN 1847	-----	According to Annex A; EN 13969
8.	Reaction to fire		EN 13501-1	----	Class E
9.	Tensile properties: maximum tensile strength -longitudinal direction, -transverse direction		EN 12311-1	N/50 mm	1500 ± 500 2500 ± 700
10.	Tensile properties: elongation -longitudinal direction, -transverse direction		EN 12311-1	%	8 ± 5 8 ± 5
11.	Flexibility at low temperature		EN 1109	°C	-15 /Ø30 mm
12.	Flow resistance at elevated temperature		EN 1110	°C	90
13.	Joint strength (shear resistance of joints) -longitudinal direction, -transverse direction		EN 12317-1	N/50 mm	1500 ± 1000 1500 ± 1000
14.	Resistance to tearing (nail shrank) -longitudinal direction, -transverse direction		EN 12310-1	N	500 ± 250 250 ± 100
15.	Resistance to impact		EN 12691 Method A Method B	mm	2000 NPD
16.	Resistance to static loading		EN 12730 Method B	kg	10
17.	Water vapour transmission properties		EN 13707	----	μ=20 000

(*) there is a possibility to produce the sheet of different length and/or width on condition that the length and/ or width specified in tests is not lower than declared.