

**Product Data Sheet**

No.: IT-6/2018/eng rev.2

Date: 20.02.2020

Page: 1/2

**BMI Icopal Sp. z o.o.**  
98-220 Zduńska Wola  
ul. Łaska 169/197  
Poland**VILLAS V60 S30**

**1. Product trade name:** Base bitumen sheet VILLAS V60 S30

**2. Technical specification:**

PN-EN 13707 + A2:2012 IDT. EN 13707:2004 + A2:2009

Flexible sheets for waterproofing – Reinforced bitumen sheets for roof waterproofing –  
Definitions and characteristics

**3. Manufacturer:** BMI Icopal Sp. z o.o., 98-220 Zduńska Wola ul. Łaska 169/197, Poland

**4. Description of the product:**

sheet with glass fleece reinforcement, coated with bitumen with filler. Top side is finished with sand,  
bottom side is profiled in order to achieve the guarantee of firm and safe bonding, and finished with foil.

**5. Type of application:** base layer, for multilayer applications in roof waterproofing

**6. Method of application:** torch applied

**7. Information for users:**

Conditions of application:

the roofing sheet should be applied on a roof when the temperature does not fall below 0 °C (prepare  
the rolls before application: store at +15 °C for min. 24 h). It should not be applied: on a wet roof  
surface, on a roof covered with ice, during rain or snow falls or during strong wind.

Conditions of usage:

waterproofing made with the use of VILLAS V60 S30 should be done according to a technical project  
complying with binding building regulations and detailed guidelines included in the manual issued by  
the producer.

Storage:

the rolls should be stored in rooms and should be protected against moisture and exposure to sunlight  
or source of heat. The rolls should be stored on an even surface in upright position, in one layer.

Transport:

the rolls should be transported in covered trucks, in upright position in one layer, protected against  
falling over and any other damage. Rolls should be placed in a way preventing their dislocation during  
transport.



**8. Product performance:**

	<b>Characteristic</b>	<b>Test method/ Classification</b>	<b>Units</b>	<b>Value or statement</b>
1.	Visible defects	EN 1850-1	----	no visible defects
2.	Length (*)	EN 1848-1	m	≥ 10
3.	Width (*)	EN 1848-1	m	≥ 1
4.	Straightness	EN 1848-1	----	deviation: ≤20 mm / 10 m or proportional for other lengths
5.	Thickness	EN 1849-1	mm	3,0 ± 15%
6.	Watertightness	EN 1928	----	watertight
7.	Reaction to fire	EN 13501-1	----	NPD
8.	Tensile properties: maximum tensile strength -longitudinal direction, -transverse direction	EN 12311-1	N/50 mm	400 ± 100 300 ± 100
9.	Tensile properties: elongation -longitudinal direction, -transverse direction	EN 12311-1	%	4 ± 2 4 ± 2
10.	Flexibility at low temperature	EN 1109	°C	0 /Ø30 mm
11.	Flow resistance at elevated temperature	EN 1110	°C	70
12.	Water vapour transmission properties	EN 13707	----	μ=20 000

(\*) there is a possibility to produce the sheet of different length and/or width on condition that the length and/ or width specified in tests is not lower than declared