

Product Data Sheet

No.: IT-4/2018/eng rev.2

Date: 20.02.2020

Page: 1/2

BMI Icopal Sp. z o.o.
98-220 Zduńska Wola
ul. Łaska 169/197
Poland**VILLAS STANDARD W-PYE PV250 S52H**

1. Product trade name: Top bitumen sheet VILLAS STANDARD W-PYE PV250 S52H

2. Technical specification:

PN-EN 13707+A2:2012 IDT. EN 13707:2004+A2:2009

Flexible sheets for waterproofing – Reinforced bitumen sheets for roof waterproofing –
Definitions and characteristics

3. Manufacturer: BMI Icopal Sp. z o.o., 98-220 Zduńska Wola ul. Łaska 169/197, Poland

4. Description of the product:

sheet with polyester fleece reinforced and stabilized with glass mesh, coated with modified bitumen with mineral filler, top side is finished with slate and with ca. 80 mm foil selvedge, bottom side is profiled in order to achieve the guarantee of firm and safe bonding, and finished with foil.

5. Type of application: top layer, for multilayer applications in roof waterproofing or single on stable basis.

6. Method of application: torch applied

7. Information for users:

Conditions of application:

the roofing sheet should be applied on a roof when the temperature does not fall below 0 °C (prepare the rolls before application: store at +15 °C for min. 24 h). It should not be applied: on a wet roof surface, on a roof covered with ice, during rain or snow falls or during strong wind.

Conditions of usage:

waterproofing made with the use of VILLAS STANDARD W-PYE PV250 S52H should be done according to a technical project complying with binding building regulations and detailed guidelines included in the manual issued by the producer.

Storage:

the rolls should be stored in rooms and should be protected against moisture and exposure to sunlight or source of heat. The rolls should be stored on an even surface in upright position, in one layer.

Transport:

the rolls should be transported in covered trucks, in upright position in one layer, protected against falling over and any other damage. Rolls should be placed in a way preventing their dislocation during transport.

Product Data Sheet

No.: IT-4/2018/eng rev.2

Date: 20.02.2020

Page:2/2

BMI Icopal Sp. z o.o.
98-220 Zduńska Wola
ul. Łaska 169/197

**8. Product performance:**

	Characteristic	Test method/ Classification	Units	Value or statement
1.	Visible defects	EN 1850-1	----	no visible defects
2.	Length (*)	EN 1848-1	m	≥ 5,0
3.	Width (*)	EN 1848-1	m	≥ 0,99 (1,00±0,01)
4.	Straightness	EN 1848-1	----	deviation: ≤ 10 mm/ 5 m or proportional for other lengths
5.	Thickness	EN 1849-1	mm	5,2 ± 10%
6.	Watertightness	EN 1928	----	watertight
7.	Reaction to fire	EN 13501-1	----	Class E
8.	Shear resistance of joints -longitudinal direction, -transverse direction	EN 12317-1	N/50 mm	700 ± 200 1000 ± 200
9.	Tensile properties: maximum tensile strength -longitudinal direction, -transverse direction	EN 12311-1	N/50 mm	1000 ± 200 700 ± 200
10.	Tensile properties: elongation -longitudinal direction -transverse direction	EN 12311-1	%	8 ± 5 8 ± 5
11.	Resistance to impact	EN 12691 Method A Method B	mm	1250 NPD
12.	Resistance to static loading	EN 12730 Method A	kg	20
13.	Dimensional stability	EN 1107-1 Method A	%	≤ 0,2
14.	Flexibility at low temperature	EN 1109	°C	0 /Ø30 mm
15.	Flow resistance at elevated temperature	EN 1110	°C	80
16.	Artificial ageing by long term exposure to elevated temperature	EN 1110 EN 1296	°C	110 ± 15
17.	Adhesion of granules	EN 12039	%	10 ± 10
18.	Water vapour transmission properties	EN 13707	----	μ=20 000

(*) there is a possibility to produce the sheet of different length and/or width on condition that the length and/ or width specified in tests is not lower than declared