



## W/PET PLUS - SBS/ICOPAL

**1. Product trade name:** Top bitumen sheet W/PET PLUS - SBS/ICOPAL

**2. Technical specification:**

PN-EN 13707 + A2:2012 IDT. EN 13707:2004 + A2:2009

Flexible sheets for waterproofing – Reinforced bitumen sheets for roof waterproofing –  
Definitions and characteristics

**3. Manufacturer:** BMI Icopal Sp. z o.o., 98-220 Zduńska Wola ul. Łaska 169/197, Poland

**4. Description of the product:**

sheet with reinforced polyester fleece reinforcement, coated with modified bitumen with mineral filler, top side is finished with slate bottom side is finished with foil.

Additional top and bottom sides of the membrane have 80 mm bitumen selvages with removable siliconized film, for connection one roll with another during application.

**5. Type of application:** top layer, for multilayer applications in roof waterproofing.

Also as a temporary waterproofing protection on full boarding or OSB board covering, for a period not longer than 12 months before the final covering, such as: tiles, metal tiles, bituminous shingles.

**6. Method of application:** with bitumen glue or mechanically: roofing nails, screws, etc.

**7. Information for users:**

Conditions of application:

the roofing sheet should not be applied: on a wet roof surface, on a roof covered with ice, during rain or snow falls or during strong wind.

Conditions of usage:

waterproofing made with the use of W/PET PLUS - SBS/ICOPAL should be done according to a technical project complying with binding building regulations and detailed guidelines included in the manual issued by the producer.

Storage:

the rolls should be stored in rooms and should be protected against moisture and exposure to sunlight or source of heat. The rolls should be stored on an even surface in upright position, in one layer.

Transport:

the rolls should be transported in covered trucks, in upright position in one layer, protected against falling over and any other damage. Rolls should be placed in a way preventing their dislocation during transport.



### 8. Product performance:

	Characteristic	Test method/ Classification	Units	Value or statement
1.	Visible defects	EN 1850-1	-----	No visible defects
2.	Length (*)	EN 1848-1	m	≥ 15
3.	Width (*)	EN 1848-1	m	≥ 0,99 (1,00 ± 0,01)
4.	Straightness	EN 1848-1	-----	deviation: ≤30 mm / 15 m or proportional for other lengths
5.	Thickness	EN 1849-1	mm	2,3 ± 0,2
6.	Watertightness	EN 1928	-----	Watertight at 10 kPa
7.	Reaction to fire	EN 13501-1	-----	Class E
8.	Tensile properties: maximum tensile strength -longitudinal direction, -transverse direction	EN 12311-1	N/50 mm	450 ± 150 350 ± 150
9.	Tensile properties: elongation -longitudinal direction, -transverse direction	EN 12311-1	%	30 ± 15 35 ± 15
10	Resistance to tearing (nail shank) -longitudinal direction, -transverse direction	EN 12310-1	N	250 ± 100 250 ± 100
11	Dimensional stability	EN 1107-1 Method A	%	< 0,2
12.	Flexibility at low temperature	EN 1109	°C	- 10 / Ø30 mm
13.	Flow resistance at elevated temperature	EN 1110	°C	85
14.	Artificial ageing by long term exposure to elevated temperature	EN 1110 EN 1296	°C	115 ± 15
15.	Adhesion of granules	EN 12039	%	20 ± 10
16.	Water vapour transmission properties	EN 13707	-----	μ=20 000

(\*) There is a possibility to produce the sheet of different length and/or width on condition that the length and/ or width specified in tests is not lower than declared.